Moravia

TECHNICAL DATA SHEET

Document No / Rev. TDS 031 / 00
Date 10.06.2009
Page No 1 / 2



Morakor

Product Description

Morakor is a chlorinated rubber based, quick drying top coat. The product offers good color retention and weathering resistance.

Intended Uses

Top coat for chlorinated rubber and epoxy based systems. It is suitable for steel, aluminium and wood surfaces.

Physical Properties

Physical State : Liquid

Colour : Moravia Catalogue Volume Solid (%) : 40 ± 2

Volume Solid (%): 40 ± 2 Density: $1,35 \pm 0,1 \text{ kg/L}$ Gloss: Semi glossFlexibility: Good

Application Data

Mixing Ratio (volume) : Single component

Application Methods: Airless spray, conventional spray, brush or roller

Application Conditions: The temperature of the substrate should be minimum 3°C above the

dew point of the air. Good ventilation is required.

Thinner/Cleaner : Moravia 019 Thinner

Guiding data for airless spray

Pressure at nozzle : 15 MPa (150 kp/cm² 2100 psi)
Nozzle tip : 0.38-0.53 mm (0.015-0.021")

Spray angle : 40-80°

Filter : Check to ensure that filters are clean.

Typical film thickness

Maximum thickness

Dry (µm)	Wet (µm)	Theoretical Coverage (m²/L)	
40	100	10,00	
60	150	6,67	

Moravia

TECHNICAL DATA SHEET

Document No / Rev. TDS 031 / 00
Date 10.06.2009
Page No 2 / 2

Surface Preparations

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Steel surface

Blast-cleaning to Sa $2\frac{1}{2}$ (ISO-8501). Power tool cleaning to min. St 2 (ISO 8501) may be acceptable, subject to exposure conditions.

Coated surface

Please contact Moravia office for further information.

Drying Time

Substrate	Touch Dry	Hard Dry	Over coating Data	
Temperature			Minimum	Maximum
10°C	1 hrs	24 hrs	8 hrs	
23°C	30 min	12 hrs	4 hrs	-
35°C	20 min	8 hrs	3 hrs	

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Packing Size : 20 kg

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Disclaimer: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.