Morakyd Primer



Product Description

Morakyd Primer is an alkyd based primer pigmented with zinc phosphate and auxiliary anti-corrosive pigments for the protection of steel structures against corrosion.

Intended Uses

Γ

As a primer for steel, aluminium and wood structures as part of a suitable alkyd system.

hysical State	: Liquid	
Colour	: Grey	
Volume Solid (%)	: 52 ± 2	
Density	: 1,3 ± 0,1 kg/L	
Gloss	: Matt	
Flexibility	: Good	

Mixing Ratio (volume) Application Methods Application Conditions	 Single component Airless spray, conventional spray, brush or roller The temperature of the substrate should be minimum 3°C above dew point of the air. Good ventilation is required. 				
Thinner/Cleaner	: Moravia 009 Thinner				
<u>Guiding data for airless s</u>	sprav				
Pressure at nozzle	: 15 MPa (150 kp/cm² 2100 psi)				
Nozzle tip	: 0.38-0.53 mm (0.015-0.021")				
Spray angle	: 40-80°				
Filter	· Chook to one				
- iiter	. Check to ens	sure that filters a	are clean.		
- iiter	Dry (µm)	Wet (µm)	Theoretical Coverage (m²/L		
Filter Fypical film thickness		1	Т		

Surface Preparations

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Steel surface

Blast-cleaning to Sa $2\frac{1}{2}$ (ISO-8501). Power tool cleaning to min. St 2 (ISO 8501) may be acceptable, subject to exposure conditions.

Coated surface

Please contact Moravia office for further information.

Drying Time

		Over coating Data	
Touch Dry	Hard Dry	Minimum	Maximum
3,5 hrs	22 hrs	22 hrs	
2,5 hrs	6 hrs	16 hrs	-
1 hour	4 hrs	10 hrs	
-		3,5 hrs 22 hrs 2,5 hrs 6 hrs	Touch DryHard DryMinimum3,5 hrs22 hrs22 hrs2,5 hrs6 hrs16 hrs

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Packing Size : 20 kg

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Disclaimer: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Fevzi Cakmak Cad. No: 2 Sefakoy / Kucukcekmece / Istanbul / Turkey Tel: +90 212 5791336 Fax: +90 212 4265512 Web: www.moraviapaint.com